

IH830C

Description

Appropriate for injection molding
High-heat grade with high chemical resistance
Good mechanical strength, surface hardness, weather resistance(AMECA listed)
Free colorability due to crystal clarity

Application

Windows for electric home appliances, Exterior/interior lighting lenses, Car tail lamps
Side mirror repeat lamp, Emblem, Car instrument clusters

Table

항목	조건	단위	검사방법	값
광학적 성질				
굴절률	nd	-	ISO 489	1.49
광투과율	3mm	%	ISO 13468-1	92
Haze	3mm	%	ISO 14782	<0.5
열적 성질				
유동성	230°C/3.8kg	g/10mn	ISO 1133	2.0
VICAT 연화점	B/50	°C	ISO 306	108
열변형온도_annealed	1.8MPa	°C	ISO 75	100
선팅창계수	-	1/°C	ASTM D696	6.5x10 ⁻⁵
기계적 성질				
Charpy 충격강도	notched	kJ/m2	ISO 179	1.5
Rockwell 경도	M scale	-	ISO 2093-2	97
인장강도 at Break	5mm/min	MPa	ISO 527	74
인장신율 at Break	5mm/min	%	ISO 527	6.5
인장탄성률	1mm/min	GPa	ISO 527	3.4
굴곡강도	2mm/min	MPa	ISO 178	113
굴곡탄성률	2mm/min	GPa	ISO 178	3.0
일반 성질				
비중	-	g/cm ³	ISO 1183	1.19
성형수축률	-	%	ASTM D955	0.2-0.6
수분흡수율	24hr	%	ASTM D570	0.3
Flammability (UL94)	1.5mm	Class	IEC 60695-11-10	HB
추천 가공 조건				
예비 건조 온도	제습 건조	°C	-	80-90
예비 건조 시간	제습 건조	hr	-	4-6
용융 온도	-	°C	-	220-250
금형 온도	-	°C	-	50-70

REMARKS : The listed values should be used for reference purpose only.