

PMMA

Injection Grade

IH830XT

Description

Appropriate for injection molding

Heat resistance grade

Excellent weatherability with optical properties (AMECA listed)

Free colorability

Mold flow simulation data is available

Application

Windows for electric home appliances, Exterior/interior lighting lenses, Inner lens

Light pipe/guide, Head lamp aspherical lens

Table

PROPERTY	CONDITION	UNIT	METHOD	VALUE
OPTICAL PROPERTIES				
Refractive Index	nd	-	ISO 489	1.49
Light Transmittance	3mm	%	ISO 13468-1	92
Haze	3mm	%	ISO 14782	<0.5
THERMAL Properties				
Melt Flow Index	230°C/3.8kg	g/10min	ISO 1133	1.8
VICAT Softening Temperature	B/50	°C	ISO 306	117
Heat Deflection Temperature_Annealed	1.8MPa	°C	ISO 75	106
Coefficient of Linear Expansion	-	1/°C	ASTM D696	6X10 ⁻⁵
MECHANICAL PROPERTIES				
Charpy Impact Strength	notched	kJ/m2	ISO 179	1.6
Rockwell Hardness	M scale	-	ISO 2093-2	99
Tensile Strength at Break	5mm/min	MPa	ISO 527	71
Tensile Strain at Break	5mm/min	%	ISO 527	4.0
Tensile Modulus	1mm/min	GPa	ISO 527	3.3
Flexural Strength	2mm/min	MPa	ISO 178	115
Flexural Modulus	2mm/min	GPa	ISO 178	3.2
GENERAL PROPERTIES				
Density	-	g/cm ³	ISO 1183	1.19
Mold Shrinkage	-	%	ASTM D955	0.2-0.6
Water Absorption	24hr	%	ASTM 570	0.3
Flammability UL94	1.5mm	Class	IEC 60695-11-10	HB
RECOMMENDED PROCESSING CONDITIONS				
Predrying Temperature	-	°C	-	80-90
Predrying Time	-	hr	-	4-6
Melt Temperature	-	°C	-	220-250
Mold Temperature	-	°C	-	50-70

REMARKS : The listed values should be used for reference purpose only.