

LX MMA Corp.

Tech-Team 58 Yeosusandan 4-ro Yeosu-si, Jeollanam-do 59613 Republic of Korea

SMMA: HX238, HX700

Polymethyl Methacrylate/Polystyrene (PMMA/PS), pellets



Flammability	Value	Test Method
Flame Rating		
1.5 mm, NC	НВ	UL 94
3.0 mm, NC	НВ	UL 94
3.0 mm, NC	HB40	IEC 60695-11-10, -20
1.5 mm, NC	HB75	IEC 60695-11-10, -20
Thermal	Value	Test Method
RTI Elec		UL 746B
1.5 mm	50.0 °C	
3.0 mm	50.0 °C	
RTI Imp		UL 746B
1.5 mm	50.0 °C	
3.0 mm	50.0 °C	
RTI Str		UL 746B
1.5 mm	50.0 °C	
3.0 mm	50.0 °C	

UL and the UL logo are trademarks of UL LLC Copyright © 2021 All Rights Reserved. | www.ul.com