

PMMA Impact Resistant Grade

HI555

Description

High impact resistance grade

High light transmission

Good mechanical strength, surface hardness, weather resistance

Free colorability due to crystal clarity

Application

Home appliance cover housing & front door, Multi-wall sheet, Corrugated sheet

Edgebands for furniture, Profile for lighting, Bath tubs

Table

項目	條件	單位	試驗方法	数值
光学性质				
折射率	nd	-	ISO 489	1.49
透光率	3mm	%	ISO 13468-1	91
雾度	3mm	%	ISO 14782	<1.5
热性质				
流动性	230°C/3.8kg	g/10min	ISO 1133	4.3
VICAT 軟化点	B/50	°C	ISO 306	85
热变形温度	1.8MPa	°C	ISO 75	84
线膨胀系数	-	1/°C	ASTM D696	7X10 ⁻⁵
机械性质				
Charpy 冲击强度	notched	kJ/m ²	ISO 179	5.8
Rockwell 硬度	M scale	-	ISO 2039-2	51
拉 拉伸强度	5mm/min	MPa	ISO 527	38
延伸率率	5mm/min	%	ISO 527	45
拉伸模数	1mm/min	GPa	ISO 527	1.6
弯曲强度	2mm/min	MPa	ISO 178	65
弯曲模数	2mm/min	GPa	ISO 178	1.8
一般性质				
比重	-	g/cm ³	ISO 1183	1.17
成型收缩率	-	%	ASTM D955	0.4-0.8
水分吸收率	24hr	%	ASTM D570	0.4
阻燃性能 (UL94)	1.5mm	Class	IEC 60695-11-10	HB
压出成型条件				
预备干燥 温度	除湿干燥	°C	-	60-70
预备干燥 时间	除湿干燥	hr	-	4-6
熔化温度	-	°C	-	210-240
模具温度	-	°C	-	50-70

REMARKS : The listed values should be used for reference purpose only.